

測定日 : 2015年10月 1日 (校正: 2015年10月 1日)

気温 26°C / 湿度 62% / 気圧 1001hPa

KEC法(磁界) 100kHz~1GHz: Radia Shield Fabric 20150918

# Freq[MHz]	シールド効果(dB)	シールド効果(%)	遮蔽率(%)
0.1	0.3	96.6050879	3.394912101
0.15	0.3	96.6050879	3.394912101
0.2	0.3	96.6050879	3.394912101
0.3	0.3	96.6050879	3.394912101
0.5	0.3	96.6050879	3.394912101
0.75	0.3	96.6050879	3.394912101
1	0.3	96.6050879	3.394912101
1.5	0.2	97.7237221	2.276277904
2	0.3	96.6050879	3.394912101
3	0.3	96.6050879	3.394912101
5	0.4	95.4992586	4.500741398
7.5	0.7	92.25714272	7.742857285
10	0.9	90.15711376	9.842886239
15	1.5	84.13951416	15.86048584
20	2.3	76.73614894	23.26385106
30	3.9	63.82634862	36.17365138
50	6.6	46.77351413	53.22648587
75	9.3	34.27677865	65.72322135
100	11.3	27.22701308	72.77298692
150	14.2	19.498446	80.501554
200	16.4	15.13561248	84.86438752
300	19.2	10.96478196	89.03521804
500	22.7	7.328245331	92.67175467
750	25.7	5.188000389	94.81199961
1000	29	3.548133892	96.45186611
		平均値	34.41097736